

Concrete Reinforcement



REBAR Reinforcing Steel Bars – Grade 60

In-stock sizes: #3, #4, #5, and #6. 20-ft. lengths.

ASTM Standard Reinforcing Bars

Bar Size	Imperial		Weight Lb. / Ft.	Soft Metric		
	Fraction	Decimal		Bar Size	Dia. mm	Weight Kg / Ft.
#3	3/8	0.375	0.376	#10M	9.5	0.171
#4	1/2	0.500	0.668	#13M	12.7	0.303
#5	5/8	0.625	1.043	#16M	15.9	0.473
#6	3/4	0.750	1.502	#19M	19.1	0.681
#7	7/8	0.875	2.044	#22M	22.2	0.927
#8	1	1.000	2.670	#25M	25.4	1.211
#9	1-1/8	1.128	3.400	#29M	28.7	1.542
#10	1-1/4	1.270	4.303	#32M	32.3	1.952
#11	1-3/8	1.410	5.313	#36M	35.8	2.410
#14	1-3/4	1.693	7.650	#43M	43.0	3.470
#18	2-1/4	2.257	13.600	#57M	57.3	6.169

Grades and Minimum Yield Strengths

Imperial		Soft Metric	
Grade	Min. Yield Strength	Grade	Min. Yield Strength
40	40,000 PSI	300	300 MPa (43,400 PSI)
60	60,000 PSI	420	420 MPa (60,900 PSI)
75	75,000 PSI	520	520 MPa (75,400 PSI)


Rebar Covers

Exposed rebar, pipe, threaded rod, shebolts, etc., create potential hazards which can result in employee injury and lost time.



OSHA Approved

Bar Guards



Round Nail Stakes (3/4", 7/8")



Lengths available:
18", 24", 30" and 36"

Nails

Types available:



Box



Common



Duplex



Concrete

Division
3